

C2ETS2 Premium Quality, Flexible, Polymer Modified, Cement Based Tile Adhesive

DESCRIPTION

ACT ADH-55 is a high strength, premium quality, flexible, polymer modified, cement based tile adhesive used for wall & floor applications. Recommended over concrete, green screed, cement render, fibrous cement sheeting, plasterboard as well as **ACT WP-1** and **ACT Australia** approved under tile waterproofing membranes.

FEATURES & BENEFITS

- ◇ **C2**-High Adhesion Strength
- ◇ **E**- Extended Open Time
- ◇ **T**- Non Slip/Non Slump
- ◇ **S2**-Highly Deformable Adhesive
- ◇ ≤1mm crack bridging capability

SUITABLE FOR

- ◇ Swimming Pools
- ◇ Concrete (after 7 days)
- ◇ Sand & cement screeds
- ◇ Green Screeds
- ◇ Rendered surfaces
- ◇ Rendered Block & Brickwork
- ◇ Fibrous cement sheeting
- ◇ Plasterboard
- ◇ Existing tiles
- ◇ ACT Australia approved under tile waterproofing membranes.
- ◇ Areas covered under AS3958.1-2007

PERFORMANCE DATA

Exceeds the performance requirements of AS4992
Tensile adhesive strength ≤1.0MPa (28 days)

COVERAGE

20kg bag will cover 8.5m² with 10mm notch trowel

SUBSTRATE PREPARATION

All substrates to be tiled must be clean, dry, free from dust, wax, oil, grease, laitance, curing compounds, paints (inc overspray), coatings and all contaminants which may cause adhesion failure. Fibrous cement sheeting & plasterboard must be fixed as per manufacturers recommendations and should be sponged down with clean water to remove dust. Waterproof boards such as Scyon Secura and Cemintel Constructafloor must be primed with **ACT PR-1** or if in wet area waterproofed with **ACT WP-1**. Ensure all dust is removed prior to spreading adhesive. **ACT WP-1** or **ACT Australia** approved under tile waterproofing membranes must be fully cured prior to tiling. Concrete must be cured for 7 days. Sand and cement screeds and renders must be cured for 24hrs. If in doubt with any of above please contact **ACT Australia Technical Services**.

PRIMING

In normal circumstances no priming is required as **ACT ADH-55** has unique Infused Primer Technology (**IP**T). To test substrate sponge liberal amounts of water onto the substrate and ensure water absorption is taking place. If so, then only sponge down with clean water prior to spreading adhesive. If water is beading or no absorption is taking place then prime with **ACT PR-1** impervious primer.

MIXING

20kg of **ACT ADH-55** powder will require approximately 5 litres of clean drinking water. Slowly add **ADH-55** powder into a clean bucket with the measure water. Slowly mix with a drill & quality mixing paddle to ensure a smooth lump free tooth paste consistency. Leave the mix for 4 minutes then re-stir. The adhesive is now ready for use.

MOVEMENT JOINTS

Movement joints must be incorporated within the tiling system in accordance with AS3958.1-2007. Ensure movement joints are free of all adhesive and grout residue.

APPLICATION

All workmanship must be in accordance with AS3958.1-2007. After mixing adhesive, apply the adhesive with the appropriate size notch trowel for the application. Ensure to work the adhesive to the substrate for good adhesion. Adhesive should sit up and not slump whilst being wet and tacky prior to laying tiles. Open time is approximately 30 mins at 23°C. If the adhesive has skinned over prior to laying tiles then remove and apply fresh adhesive. Ensure minimum adhesive bed thickness is 2mm for wall & 4mm for floor applications depending on size of tile.

DRYING

Allow minimum 24hrs for the adhesive to cure and set prior to grouting. For impervious substrates such as waterproofing membranes and or non-absorbent tiles further curing time will be required depending site conditions and ambient temperatures. Ensure adhesive has set prior to grouting.

GROUTING

Use ACT Australia recommended grouts. Ensure grout joints are clean of any adhesives residue prior to mixing grout with clean water to a toothpaste consistency.

SHELF LIFE

In unopened original packaging for up to 12mths when stored in a cool, dry environment off the floor.

SAFETY DIRECTIONS

ACT Australia supports best practise in material handling. Appropriate gloves, dust masks, safety glasses and protective clothing should be worn. If product comes in contact with skin, wash off with soapy water. Avoid inhaling dust by wearing appropriate dust mask. If swallowed, drink plenty of drinkable water and seek medical advice. In case of contact with the eyes, rinse with clean water or eye wash solution and seek medical advice.

LIMITATIONS

- ◇ Not suitable for tiling directly over 100% polyurethane or fibreglass waterproofing membranes.
- ◇ Not suitable for tiling directly over plastics and metals.
- ◇ Not suitable for tiling directly over Masonite, MDF, timber, plywood or particleboard.
- ◇ Not suitable for moisture sensitive stone such as green marble or manmade conglomerate products.
- ◇ External tiling should not exceed 2.7m in height.
- ◇ Suspended concrete slabs must conform to AS3958.1-2007 for maximum deflection. All post-tensioned concrete slabs must be treated as flexible substrate.
- ◇ If in doubt, contact **ACT Australia Technical Services** for further information and advice.